

Overzicht rubberingestrooide kunstgrasvelden

Samenstelling: Gerrit de Koe

Marktpartij	Leverbare Types	Product / tufter	Garenleveranc	Material	Gefibrilleerd	Monofilament	Polhoogte	Material Rug
Arcadis / Edel	Edel ArenA Grass versie 1	EDEL Grass bv	TenCateThiol	PE/LSR	ja		60	sec.backing
Arcadis/ Edel	Edel ArenA Grass versie 2	EDEL Grass bv	TenCateThiol	Xtreme		ja	55	C 08
Arcadis/ Edel	Edel ArenA Grass versie	EDEL Grass bv	TenCateThiol	Xtreme		ja	55	C 08
Arcadis / Edel	Edel Nature LSR52	EDEL Grass bv	TenCateThiol	PE/LSR	ja		52	sec.backing
Arcadis / Edel	Edel Nature LSR60	EDEL Grass bv	TenCateThiol	PE/LSR	ja		60	sec.backing
Arcadis / Edel	Edel Nature LSRXP	EDEL Grass bv	TenCateThiol	PE/LSR	ja		60	sec.backing
Arcadis / Edel	Edel Soccer Performer 2004	EDEL Grass bv	TenCateThiol	PE/LSR		monotape	60	PP/Polyeth.
Arcadis/ Edel	Edel Soccer Standard	EDEL Grass bv	TenCateThiol	PE/LSR	ja		52	sec.backing
Arcadis/ Edel	Edel Soccer Standard	EDEL Grass bv	TenCateThiol	PE/LSR	ja		60	sec.backing
Arcadis / Edel	Edel Top Blade 52	EDEL Grass bv	TenCateThiol	PE/LSR		ja	52	sec.backing
Arcadis / Edel	Edel Top Blade 60	EDEL Grass bv	TenCateThiol	PE/LSR		ja	60	sec.backing
Arcadis / Edel	Edel Nature Xtreme	EDEL Grass bv	TenCateThiol	Xtreme	CLMT		60	C 08
Arcadis / Edel	Edel Xtreme / Bi-color	EDEL Grass bv	TenCateThiol	Xtreme	CLMT		60	C 08
Arcadis / Edel	Edel Xtreme / Bi-color	EDEL Grass bv	TenCateThiol	Xtreme	CLMT		40	C 08
	ThiolonXtreme 125		TenCateThiol	Xtreme	CLMT			11.000 of
	Thiolon Trimension		TenCateThiol	Xtreme	CLTM	ja+mt		C 08
Arcadis	Premium (andere verstrekking?) Lankhorst		TenCateThiol	Xtreme MF	ja	ja		
Nootenboom Sport	Final 60	LANO Sports		PE		ja	60	Thiob/PP/
Nootenboom Sport	Final M60 / Slide	Mattex						
Nootenboom Sport	Profoot plus	LANO Sports	TenCateThiol	PE			55	Thiob/PP/
Nootb/ Greenfields	FT55 Elite						56	
Nootb/ Greenfields	FT55 Elite LSR						56	
Nootb/ Greenfields	Real FT 55 fc 2005	Greenf/belacos	monofil/div.	PE/getwijnt		ja	55	Thiob./PP/glasv
Oranjewoud	(DD)OrW. Soccer Grass	Desso	Desso	PE		Ja		latex
Oranjewoud	DD Match PS-60	Desso	Desso	PE	ja		60	latex
Oranjewoud	Challenge Pro	Desso	Desso	PE		ja	60	latex
Oranjewoud	NC SoccerPro MFD60(dt) 2005	Polytan	TenCateThiol	PE/		ja	60	latex/glasv
Oranjewoud	NC SoccerPro MF	Limonta	TenCateThiol	PE		ja	(53)60	latex/glasv
Oranjewoud	NC SoccerPro MF	Limonta	TenCateThiol	PE		Ja	(53)63	latex/glasv
Oranjewoud	NC SoccerPro MF	Limonta	TenCateThiol	PE		Ja	(53)63	latex/glasv
Oranjewoud	NC Soccer Pro Top	Limonta	TenCateThiol	PE	ja	ja	(53)60	latex/glasv
Oranjewoud	NC SoccerProXtreme/S	Limonta	TenCateThiol	PE		CLMT	(53)63	latex/glasv
Oranjewoud	NC SoccerProXtreme MF	Limonta	TenCateThiol	PE		ja	(53)63	latex/glasv
Oranjewoud	OrW. NC Voetbal LSR	Polytan	TenCateThiol	PE/LSR	ja		60	latex/glasv
Oranjewoud	NC Soccer MF PE/16	Polytan	Polytan	PE		Ja	60	latex/glasv
Oranjewoud	NC Soccer MF PE/18	Polytan	Polytan	PE		Ja	60	latex/glasv
Oranjewoud	NC Soccer Pro Top 60		TenCateThiol	PE	ja	Ja	60	latex/glasv
Grontmij	GMFloor voetb. PE443(60mm) 2007	DOMO	DOMO?	PE		ja	50-60	PP/glasw/Latex
Grontmij	GMFloor voetb. PE416 2003	DOMO	Xerion	PE	ja		52 mm	PP/glasw/Latex
Grontmij	GMFloor voetb. PE231 2003			55				
Grontmij	GMFloor voetb. PE232 2003	DOMO	Xerion	PE	ja		50 mm	PP/Latex
Grontmij	GMFloor voetb. PE473 2003	DOMO	Xerion	PE	ja en monofil.		60 mm	PP/glasw/Latex
Heimans / Desso	DD Challenge Pro ² 60 2007	Desso	Desso	PE		ja	60 mm.	PP/polyest.vlies
Heimans / Desso	DD Soccergrass TD50	Desso	Desso	PE		ja	50 mm	PP/polyest.vlies
Heimans / Desso	DD Soccergrass TD60	Desso	Desso	PE		ja	60 mm	PP/polyest.vlies
Heimans / Desso	DD Challenge (of 60)	Desso	Desso	PP		ja	50 mm	PP/polyest.vlies
Heimans / Desso	DD Match PS-50	Desso	Desso					
van Kessel	Prestige 55 / Tarkett Sommer 2003	Tarkett/Fieldt.t	TenCateThiol	PE/LSR	ja		55 mm.	PP/PA en latex
van Kessel	prestige 60 / Tarkett Sommer 2003	Tarkett/Fieldt.t	TenCateThiol	PE/LSR	ja		60 mm.	PP/PA en latex
van Kessel	Prestige 65 / Tarkett Sommer 2003	Tarkett/Fieldt.t	TenCateThiol	PE/LSR	ja		65 mm.	PP/PA en latex
van Kessel	Prestige XT 60 2004	Tarkett/Fieldt.t	TenCateThiol	XT PE	ja, linkt monof		60	PP/PA en latex
van Kessel	Prestige XT 60 / TS / dualtone	Tarkett/Fieldt.t	TenCateThiol	XT PE	CLMT		60	PP/PA en latex
van Kessel	XM60 = gelijk aan de Evolution 2005	Tarkett/Fieldt.t	Mattex	PE/LSR		ja	60	PP/PA en latex
van Kessel	V.Kessel Soccer Pro 100 LSR	Limonta T	enCateThiol	PE/LSR	ja		58	PP/PA en latex
C.S.C. Ceelen Sp.	Fieldturf 2.5	Tiger	Bonar	PE	ja		63	ThiobacPro
C.S.C. Ceelen Sp.	Fieldturf 2.5	Tiger	Bonar	PE	ja			ThiobacPro
C.S.C. Ceelen Sp.	Fieldturf Real							
C.S.C. Ceelen Sp.	Football 63	Tiger	Bonar	PE	ja		63	PP/PA en latex
C.S.C. Ceelen Sp.	Football 63	Tiger	Bonar	PE	ja			PP/PA en latex
C.S.C. Ceelen Sp.	Evolution 2005	Fieldturf/Tark.	Mattex	PE		ja	63	C 08

dtex gehalte	garandikte in micron	tape breedte	steken per m2	poolgewicht gr./m2	Poolverankering	Duurzaamheid	Tot. Steken/ends p. m2	Keuringen ISA/LABO ver. onderz.prakt= in onderz.	Kosten p. veld incl. btw	Garantie contr.of zelf	diversen
15.000	110	5 mm	8190	1,750		econ. 10 jr.		Fifa*/ ISA	460,000	onderh.c	tot.gewicht 3859 gr/m2
16.000	240	1,5 mm	10700	1,800		econ. 10 jr.		Fifa** / ISA		onderh.c	tot.gewicht 3.484 gr/m2
12000	240	1,5 mm				nog niet geïnstalleerd in Nederland		xx			
11,000	100	12 mm	9450	1,150		econ. 10 jr.		ISAcertif.	460,000	onderh.c	tot.gew\3259 gr.
11,000	100	12 mm	9450	1,330		econ. 10 jr.		ISAcertif.	460,000	onderh.c	tot.gew.\3439 gr.
11,000	100	12 mm	9450	1,300		econ. 10 jr.		ISAcertif.	460,000	onderh.c	zie map EDEL/3409 gr/m2
11.000	100	2 mm	9450	1,380				ISA/in onderz			EPDM of SBR/3039 gr/m2
11,000	100	12 mm	9450	1,150		econ. 10 jr.		ISA/in onderz	?	onderh.c	tot.gewicht 2809 gr/m2
11,000	100	12 mm	9450	1,330		econ. 10 jr.		ISA/in onderz	?	onderh.c	tot.gewicht 2989 gr/m2
11000	150	1 mm	9450	1,300		econ. 10 jr.		ISA/in onderz	?	onderh.c	tot.gewicht 2659 gr/m2
11000	150	1 mm	9450	1,580		econ. 10 jr.		ISA/in onderz	?	onderh.c	tot.gewicht 3239 gr/m2
11,000	100	12 mm	9450	1,430		econ. 10 jr.		ISA certif.		onderh.c	tot.gewicht 3.134 gr/m2
13.800	100+110	9+5mm	10800	1,870		econ. 10 jr.		Fifa** / ISA		onderh.c	tot.gewicht 3.529 gr/m2
13.800	130					i.s.m. AKAM onderbouw mat bij AGOVV en AZ)		Fifa** / ISA			
13,000	125	1 mm.									
11400	100+(7)	1+2+5				nog niet geïnstalleerd in Nederland					drie kleuren mat
12of16000	240	in midden van vezel									vezel 1,5 mm/ monofilam
14,400	160&		7875	1,530				ISA/in onderz			160&210
11,000	100		9450	1,280				ISA/in onderz			tot.gewicht 2.440 gr/m2
								ISA/in onderz			
14.000	100/120		8820	1,520				ISA/in onderz			onderb: lava /2830 gr/m2
11,000	120		8400	1,300				ISAcertif.	387,000	onderh.c	tot.gewicht 2345 gr/m2
11,000	100		8400	1,245				ISA certif.		onderh.c	tot.gewicht 2560 gr/m2
2000	200		8400	1,420				ISA/in onderz		onderh.c	tot.gewicht 2735 gr/m2
11,000	150		8135	1,350				ISA/in onderz			tot.gewicht 2575 gr/m2
1375 p.fil	150		6825	1,150				ISA/in onderz		onderh.c	tot.gewicht 2215 gr/m2
1375 p.fil	150		7875	1,325				ISA/in onderz		onderh.c	tot.gewicht 2390 gr/m2
1000 p.fil	120		8660	1,000				ISA/in onderz		onderh.c	tot.gewicht 2065 gr/m2
13,250	150/110		6825	1,300				ISA/in onderz		onderh.c	tot.gewicht 2415 gr/m2
13,800	130		7350	1,500				ISA/in onderz		onderh.c	tot.gewicht 2615 gr/m2
2000 p.fil	240		7875	1,350				ISA/in onderz		onderh.c	tot.gewicht 2465 gr/m2
11000	100		8137	1,188				ISAcertif.			tot.gewicht 2.295 gr/m2
12000(9)	>200		8400	1,300		110160		ISA certif.			tot.gewicht 2520 gr/m2
12000(9)	>200		9450	1,450		110160		ISA certif.	6 bandjes		tot.gewicht 2670 gr/m2
13,250	150/110		1300								tot.gewicht 2415 gr/m2
12,400	160	1,4 mm	6929	>1.275	30 N	>110.864					tot.gew.>2594 gr/m2
8,800	80		13858	1,450		10-12 jr.		ISAcertif	*357.000		bijz.heden zie map SBR
11,000	100		8819	1,095		10-12 jr.		ISA/in onderz	*340.000		referenties Grontmij
16,850	120		7097	1,315				ISA/in onderz	*316.000		* ex.cunet etc /2.709 gr. EPDM of SBR
12100	210		8559	tot.2.735		ca 136944		UEFA	² =kwardraad		EPDM of SBR
8,800	120		8559	tot.2.184				ISA-i.o./Labo/skz			Desso experimenteert
8,800	120		8559	1,030				ISA/Labo/skz			tot.gewicht 2.345 gr/m2
								ISA/in onderz			en FIFA aanbevolen
								ISA/in onderz			PS60 niet in sportvl.lijst
12,000	100		7560	1,198		8 jr.garant		ISA-i.o./Labo	368,000	beide	tot.gewicht 2.041 gr/m2
12,000	100		6930	1,198		8 jr.garant		ISAcert/Labo	368,000	beide	tot.gewicht 2.063 gr/m2
15,000											
14,000	120		6930	1,300		8 jr.		ISAcert.			tot.gewicht 2.480 gr/m2
14,000	120		6930	1,300		8 jr.		ISAcert.		(twee kleuren vezel)	tot.gewicht 2.480 gr/m2
11,000	120		8190	1,164		8jr.garant		ISA/in onderz		(twee kleuren vezel)	
11,000	100		8700	1,350		8 jr		ISAcert.			
8,800	100		8840	1,095				ISAcertif.			tot.gewicht 1.909 gr/m2
11,000	100		8840	1,095							
8,800	80		9450	1,160				ISAcertif.			tot.gewicht 2.124 gr/m2
11,000	100		8600	1,250							
> 14.000	110-230	2 mm	9060	> 1.350		> 100.000		ISAcertif.			tot.gew 2.560 gr/m2