LANGMUIR

Hydrolytic, Thermal, and Electrochemical Stability of Thiol- and Terminal Alkyne-Based Monolayers on Gold: A Comparative Study

Zhen Yang, Sidharam P. Pujari, Rachel Armstrong, Klaus Mathwig, Floris P. J. T. Rutjes, Maarten M. J. Smulders,* and Han Zuilhof*

Cite This: Langmuir 2025, 41, 6197–6207



Article Recommendations

ACCESS

III Metrics & More

ABSTRACT: The terminal alkyne–Au interaction is emerging as a promising adsorbing bonding motif for organic monolayers, allowing it to be used for installing antifouling layers and/or recognition elements on gold surfaces for biosensing applications. In contrast to the well-known thiol-on-gold monolayers, the long-term hydrolytic, thermal, and electrochemical stability of the alkyne–Au bond remains relatively unexplored. Insight into these is, however, essential to deliver on the promise of the alkyne–Au bond for (bio)sensing applications, and to see under which conditions they might replace thiolate–gold bonds, if the latter are insufficiently stable due to, e.g., biological thiol exchange. Therefore, these stabilities were investigated for monolayers on Au substrates formed from 1-octadecanethiol and 1-octadecyne. Additionally, monodentate and tridentate alkyne-based adsorbates were designed



to investigate the effect of multivalency on the stability. The hydrolytic stability over time in four aqueous media and the thermal stability in air were evaluated using static water contact angle measurements and X-ray photoelectron spectroscopy. Electrochemical oxidative desorption potentials were also assessed by cyclic voltammetry. All three tests indicate that the monovalent terminal alkyne monolayers on gold are slightly less stable than their thiolate analogs, which we could attribute to a lower packing density but still sufficiently stable to be applied in biosensing in the gut, while multivalency can further improve this. Our work provides insight into the stability of terminal alkynes under different conditions, better enabling the use of terminal alkyne—Au interactions in biosensors.

1. INTRODUCTION

Biosensors are gaining momentum in a wide range of applications, including clinical research, environmental monitoring, and medical diagnostics, as they often combine favorable properties such as real-time, selective, and sensitive analysis.¹ The sensing components are the focus of biosensor development both in academic and industrial research. Despite the efforts dedicated to improving sensitivity and accuracy for detecting and analyzing target analytes, a persistent challenge is biofouling, which typically exists in complicated biological matrices such as blood, feces, extracellular fluids, and intestinal fluids, hindering further development and practical applications.^{2–4} Modifying the sensing part with an antifouling coating is widely applied as an effective strategy to prevent the nonspecific adsorption of biomolecules and microorganisms.⁵⁻⁹ Organic monolayers are frequently employed as interfaces between sensing substrates and the surrounding environment. They offer advantages such as controlled reactivity, easy preparation, and the possibility to tailor the surface properties.¹⁰ In electrochemical sensors, noble metals such as gold, silver, or platinum are widely used as electrode materials due to their excellent conductivity and chemical inertness.¹¹⁻¹³ (R-SH) can spontaneously attach and selfassemble on these substrates to form ordered self-assembled monolayers (SAMs).¹⁴ Therefore, in addition to their role as standard models to investigate surface and interfacial

chemistry, thiolate SAMs have also been extensively applied for electrochemical sensors.¹⁵

The stability of coatings is crucial for biosensors' performance, and poor resistance to ambient disturbances lowers the precision and accuracy of measurements.¹ Hence, extensive research has been conducted to explore the stability of thiolate SAMs under various conditions, including exposure to air,^{16,17} aqueous solutions,^{16,18} organic solvents,¹⁶ biological media,¹⁸ and different temperature regimes.¹⁹ Although the thiolate SAM stability is affected by various factors, the oxidation of -SH group is generally recognized as the main cause of the deterioration of thiolate SAMs.^{17,20} Moreover, applying thiolate SAMs as biosensor interfaces also faces more challenges. For example, undesirable interference in the sensing process may occur due to the potential exchange of thiol ligands by abundant biological thiols under physiological conditions.^{21,22} A widely adopted solution to enhance the monolayer stability involves utilizing multidentate adsorbates.²³ These compounds possess the ability to form multiple

Received:December 20, 2024Revised:February 20, 2025Accepted:February 20, 2025Published:March 1, 2025





Scheme 1. Illustration of the Organic Monolayers Formed by C₁₈SH, C₁₈alkyne, C₁₈monoalkyne, or C₁₈trialkyne on Gold^a



 ${}^{a}C_{18}$ monoalkyne and its trivalent counterpart C_{18} trialkyne share similar chain lengths and functional groups; however, they differ in the number of binding sites.

bonds with the substrate, resulting in more strongly attached monolayers, reducing the risk of detachment (by exchange) or degradation. Diverse multidentate thiol-based adsorbates on Au substrates have been constructed and tested, and appropriately designed multidentate monolayers have been proven to have enhanced stability compared to their monosubstituted analogs.^{23–25}

In addition to the strategy of increasing the number of binding sites, tailoring the surface attachment properties can also be achieved by changing the functional headgroup. Recently, various Au-C interactions have been developed including covalent Au–C σ bonds,^{26,27} N-heterocyclic carbenes on gold^{28–30} and the terminal alkyne–Au motif.^{31,32} Among them, terminal alkynes have been increasingly studied because of the ease of preparation of these anchoring molecules, their stability in air (precluding the necessity to add reducing agents), and the mild reaction conditions required for surface attachment.^{31,33} The bonding process between terminal alkyne and gold, including the fate of the terminal hydrogen, has been reported previously,³⁴ suggesting that the mechanism involves the heterolytic deprotonation of the terminal hydrogen, and formation of an upright configuration on Au, with an accompanying weakened $C \equiv C$ bond. Moreover, the displacement experiments conducted by Landis and co-workers showed that an 1ethynyl-4-fluorobenzene monolayer on Au exhibited a higher resistance to displacement by 1-octadecanethiol compared to a 4-fluorobenzene-1-thiolate monolayer, due to the enhanced stability of the Au-C bond.³⁵ Additionally, alkyne monolayers typically exhibited a higher electrochemical transmittance compared to thiolate monolayers, which could potentially facilitate biosensor fabrication by improving signal transmission during sensing processes.^{35,36} Furthermore, the terminal alkyne-Au bonding motif has been employed in biosensors. Recently, Tian's group achieved the real-time mapping and accurate analysis of Fe²⁺ in biological conditions by attaching ferrocenyl endoperoxide carboxylic acid as a detecting unit to an Au electrode via Au−C≡C bonds, which exhibited superior performance and was less affected by biological thiol (5 mM of glutathione) compared to Au-S and Au-Se analogs.

Given this potential, detailed knowledge of the stability of $Au-C\equiv C$ bonds under a variety of hydrolytic and thermal conditions is highly relevant, yet reports on this are still scarce. To close this gap, here we investigate the stability difference between the Au-C $\equiv C$ and Au-S bonding motifs via a series of comparative experiments. First, we investigated and

compared the hydrolytic stability over time of SAMs on Au made of 1-octadecanethiol (C18SH) or 1-octadecyne $(C_{18}alkyne, see Scheme 1)$ by XPS and SWCA. The media used included water, HCl (pH 3), and NaOH (pH 11), as well as simulated intestinal fluid (SIF) to investigate the stability of the monolayers in a complex biological ionic environment, providing a reference for their future application in the gut biosensors. Second, we assessed the thermal stability by analyzing monolayer samples after heating at an elevated temperature (80 °C). Finally, their electrochemical stability was probed via measured of their oxidative potentials by cyclic voltammetry (CV) measurements. In addition to investigating the effects of the bonding motif, the impact of the number of ligands of the terminal alkyne-based monolayers was also investigated. To this aim, a novel tridentate terminal alkyne adsorbate (C18trialkyne) was synthesized, along with its monodentate analog (C_{18} monoalkyne, Scheme 1), and their stabilities were investigated.

2. EXPERIMENTAL METHODS

2.1. Chemicals and Materials. Au substrates (200 nm thick Au layer on silicon) were obtained from Ssens (The Netherlands). 1-Dodecanethiol $(C_{12}SH)$ and 1-octadecanethiol $(C_{18}SH)$ were purchased from Sigma-Aldrich and directly used for surface modification without any purification. 1-Octadecyne (C18alkyne) was synthesized according to literature procedures.³⁸ Di-tert-butyl decarbonate (Boc₂O), hydrogen peroxide (H₂O₂, 30%), hydrochloric acid (HCl, 37%), sodium hydroxide (NaOH, pellets), and anhydrous triethylamine (TEA) were purchased from Sigma-Aldrich. Ethanolamine and sodium chloride (NaCl) were purchased from VWR Chemicals. Potassium hydroxide (KOH, pellets), magnesium chloride hexahydrate (MgCl₂·6H₂O) and potassium dihydrogen phosphate (KH₂PO₄) were purchased from Boom B.V. Propargyl bromide, trifluoroacetic acid (TFA) and stearoyl chloride were purchased from TCI. Potassium chloride (KCl), 2-amino-2-hydroxymethylpropane-1,3-diol (Tris), sulfuric acid (H_2SO_4 , 96%), acetone, dimethylformamide (DMF), dichloromethane (DCM), ethanol, n-hexane, and methanol were purchased from Fisher Scientific. Petroleum ether (PE) and ethyl acetate (EA) were purchased from Labo-Scientific B.V. Ethanol used for surface modification was degassed by 3 consecutive freeze-pump-thaw (FPT) cycles. Anhydrous DCM was produced with a solvent purification system of Innovative Technology. Deionized water was produced with a Milli-Q Integral 3 system from Millipore, Molsheim, France. Simulated intestinal fluid without enzymes and Ca2+ (briefly named SIF in this paper) with pH of 7 was prepared according to literature procedures.

Au disk electrodes (1.6 mm diameter), Pt wire (0.5 mm diameter) and Ag/AgCl (in 3 M KCl) were purchased from BASi. Diamond slurries (1 and 0.25 μ m size), and alumina slurry (0.05 μ m size) were purchased from Buehler (USA).

2.2. Synthesis of Adsorbates. N-(2-(prop-2-yn-1-yloxy)ethyl)stearamide (C_{18} monoalkyne) and N-(1,3-bis(prop-2-yn-1-yloxy)-2-((prop-2-yn-1-yloxy)methyl)propan-2-yl)stearamide (C_{18} trialkyne) were synthesized according to the protocol in the Supporting Information (Section S1).

2.3. Monolayer Preparation. Au flat surfaces were first sonicated separately in HPLC-grade *n*-hexane and acetone for 5 min in each solvent, and then rinsed with DCM and dried with Ar flow. Subsequently, the Au substrates were cleaned with piranha solution $(H_2SO_4:H_2O_2 = 7:3 \text{ v/v})$ at room temperature (20 °C) for 10 min, then washed with copious amounts of Milli-Q (MQ) water, immersed in ethanol for 10 min, and dried using argon flow. [Caution!"*Piranha*" solution can react violently with organic substances, so please use with extreme caution.] Au disk electrodes were first cleaned by sequential polishing with 1 and 0.25 μ m diamond slurries, followed by 0.05 μ m alumina slurry for a minimum of 1 min each. The electrodes were then rinsed with MQ water and ethanol, sonicated in MQ water for 3 min, immersed in piranha solution for 3 min, washed with copious amounts of MQ water, rinsed with EtOH, and dried with an Ar flow.

The Au substrates were immersed into 1 mL of ethanolic solutions of adsorbates (5 mM) in glass vials in an O₂-free glovebox (SteDa Kunststoftechniek B.V.) with an O₂ content of less than 1%. The thiolate monolayer formed at room temperature (20 °C) for 16 h, while the terminal alkyne monolayers were prepared at 60 °C for the same duration of time. Subsequently, the surfaces were rinsed with ethanol and *n*-hexane, then blown dried with an Ar flow. The monolayers formed on Au flat surfaces were characterized by SWCA and by XPS for quality control before hydrolytic and thermal stability tests.

2.4. Hydrolytic Stability Tests. The hydrolytic stability of the organic monolayers was evaluated through immersion in different media (1 mL media solution per surface), namely MQ-water, SIF (pH 7), HCl aqueous solution (pH 3), and NaOH aqueous solution (pH 11), for varying durations of 0, 1, or 7 days. All surfaces were placed with their Au side facing down on the vial bottom in the individual sealed glass vials to ensure complete contact with the solution. The vials were placed in the incubator shaker (Benchtop Innova 4080) at 25 rpm and a constant temperature of 25 °C. Before measurement, the surfaces were washed with MQ-water and then sonicated in ethanol for 10 s individually, and then the surfaces were subsequently rinsed with DCM and blown dry with an Ar flow. Three parallel surfaces were prepared for subsequent water contact angle and XPS measurements for each condition.

2.5. Thermal Stability Tests. To assess the thermal stability of the modified organic monolayers, the surfaces were placed in glass vials and exposed to various temperatures ($80 \,^{\circ}$ C) for 1 or 16 h in a heating oven (Carbolite Gero). The vials were not sealed and left open to the air. After heating, samples were washed with MQ-water and then sonicated in ethanol for 10 s, then rinsed with DCM and dried with an Ar flow. For each condition, three parallel surfaces were prepared for subsequent measurements of water contact angle and XPS.

2.6. Electrochemical Stability Tests. Electrochemical measurements were conducted on a PalmSens4 portable electrochemical workstation using an electrochemical cell from BASi in a threeelectrode configuration. Ag/AgCl (in 3 M KCl) was used as the reference electrode and a Pt wire as the auxiliary electrode. The electrochemical oxidative potentials of the bare/modified Au disk electrodes (1.6 mm diameter) as working electrodes were measured by CV measurements in 0.1 M H_2SO_4 aqueous solution. The potential was scanned at 0.05 V/s starting from 0 to 1.5 V and then scanned back to 0 V.

2.7. Surface Analysis Tools. 2.7.1. SWCA Measurement. The Krüss DSA 100 contact angle goniometer was employed to measure the wettability of the samples. The volume of the deionized water drop is 2.0 μ L. The tangent 2 fitting model was used for the contact angle measurement of all samples. Water contact angle measurements were performed before the XPS to ensure the quality of the monolayers.

2.7.2. X-ray Photoelectron Spectroscopy. A JPS-9200 photoelectron spectrometer (JEOL, Japan) was used to perform all XPS measurements, with a monochromatic Al K α X-ray source (10 kV and 20 mA). The analyzer pass energy was set to 50 eV for wide scans and 10 eV for narrow scans of C 1s. The incident X-ray angle was 10°, and the takeoff angle (φ) between the sample and detector was 80°. The measurements were processed at 1 × 10⁻⁶ Torr. All data were analyzed with CasaXPS software (version 2.3.26).

2.7.3. Atomic Force Microscopy. Under ambient conditions, AFM imaging was performed using an MFP-3D-BIO AFM (Asylum Research, Oxford Instruments) operating in tapping mode. The imaging utilized aluminum reflex-coated NCHR-16 cantilevers (NANOSENSORS, Neuchatel, Switzerland) with a tip radius of <10 nm, a frequency of 330 kHz, and a force constant of 42 N/m. Images were captured at a resolution of 512×512 pixels with a scanning rate of approximately 1 Hz.

2.7.4. Ellipsometry. The ellipsometric thickness of the monolayers was measured using an AccurionNanofilm_EP4 Imaging Ellipsometer (Park Systems), operating at 562.9–642.3 nm at an angle of incidence of 50° in the air at room temperature. Each sample was measured at three different areas, and the average values were reported. The acquired data were fitted using EP4 software employing a multilayer isotropic model that included the ambient, monolayer, and substrate, with a clean gold surface used as the substrate. The monolayers were characterized using a Cauchy model with a parameter of refractive index (A = 1.45).

3. RESULTS AND DISCUSSION

3.1. Monolayer Preparations. 3.1.1. Au Substrate Cleaning. Choosing a proper surface cleaning method is crucial for the formation of high-quality monolayers since the Au substrate is easily contaminated. Therefore, the Au substrate cleaning approaches were first investigated. In brief, we explored two commonly used methods: Au substrates were cleaned either by immersing in piranha solution for 10 min,⁴⁰ or by air plasma,⁴¹ followed by thorough washing with water and immersion in EtOH for 10 min. Both methods proved effective in reducing organic contaminants, as evidenced by the minor carbon content on the Au substrates (SI Figure S9). However, in contrast to the Au surface subjected to piranha solution, the Au surface treated with air plasma exhibited a higher oxygen content, which might be attributed to the presence of a partial oxide (Au_2O_3) thin layer on the Au substrate.⁴²⁻⁴⁴ Subsequently, 1-dodecanethiol $(C_{12}SH)$ was self-assembled to form a thiolate SAM $(Au-C_{12}SH)$ on both types of Au substrates inside an oxygen-free glovebox. The XPS spectrum revealed that the abundant oxygen content remained in the Au-C₁₂SH formed on air plasma-cleaned Au substrate, while the oxygen content was greatly reduced for the Au surface cleaned with piranha solution. Therefore, we chose 10 min of piranha solution cleaning to eliminate the potential influence of oxygen on the monolayers' stability.

3.1.2. Monolayer Formation on Au Substrates. To compare the stability of thiolate and terminal alkyne self-assembled monolayers, 1-octadecanethiol ($C_{18}SH$) and 1-octadecyne ($C_{18}alkyne$) were first allowed to self-assemble on gold surfaces. Additionally, monodentate ($C_{18}monoalkyne$) and tridentate ($C_{18}trialkyne$) alkyne-terminated adsorbates were synthesized (SI Scheme S1), and analogously allowed to form monolayers on gold surfaces, to understand the impact of multidentate structures on the stability of terminal alkyne monolayers. Monolayers were prepared by immersing freshly cleaned Au substrates in 5 mM of ethanolic solutions of each of the four adsorbents for 16 h (Scheme 1). All surface modifications were carried out inside an oxygen-free glovebox

to minimize oxidation of either the alkyne or thiol groups during the immobilization reaction; thiols were self-assembled at room temperature, and alkynes at 60 °C according to literature.³² The monolayers were first characterized by SWCA measurements, and subsequently analyzed with XPS to check the quality of the prepared monolayers (Table 1 and Figure 1A).

Table 1. Overview of Results of XPS and SWCA Characterization of Monolayers on Au Substrates

substrate-monolayer	adsorbate's molecular formula	C 1s/Au 4f signal ratio ^a	SWCA ^b (°)
Au-C ₁₈ SH	C18H38S	1.55 ± 0.07	111 ± 1
Au–C ₁₈ alkyne	$C_{18}H_{34}$	1.14 ± 0.09	102 ± 2
Au–C ₁₈ monoalkyne	$C_{23}H_{43}NO_2$	1.11 ± 0.03	101 ± 3
Au-C ₁₈ trialkyne	$\mathrm{C}_{31}\mathrm{H}_{51}\mathrm{NO}_4$	1.33 ± 0.08	99 ± 2
^a Averaged values of (a	t least) 3 samples	are reported.	^b Averaged

values of (at least) 10 samples are reported.

The SWCA of Au–C₁₈SH was 111 ± 1°, which was higher than the SWCA of Au–C₁₈alkyne, determined at 102 ± 2°. The difference in wettability is attributed to a higher packing density in the Au–C₁₈SH as compared to its Au–C₁₈alkyne counterpart.⁴⁵ This is borne out by a quantitative XPS analysis, in which the Au–C₁₈SH revealed a higher C 1s/Au 4f signal ratio of 1.55 compared to the value for Au–C₁₈alkyne at 1.14. Based on these two values, the relative packing density of the alkyne monolayer is 74% relative to its thiol counterpart. This difference in packing densities also shows up in the ellipsometric thicknesses: for Au–C₁₈SH this is 2.2 ± 0.1 nm, which aligns with the reported data (2.3 nm)²⁵ and its theoretical thickness (2.3 nm, Chem3D). For Au–C₁₈alkyne, it is 1.8 ± 0.1 nm, which is slightly lower than its theoretical thickness (2.1 nm, Chem3D). Moreover, an O 1s/C 1s signal ratio (0.04 ± 0.03) was observed in Au–C₁₈alkyne, consistent with the reported O 1s/C 1s signal ratio (<0.06) of terminal *n*-alkynes (HC≡C(CH₂)_nCH₃, *n* = 5, 7, 9, and 11) SAMs on Au.³² This presence of oxygen can be explained by partial oxidation of the alkyne head groups even upon construction in a glovebox, contributing to reduced ordering and packing density, as previously reported.³² These observations are similar to findings in the literature, which reported that the packing density of an aromatic alkyne monolayer is ca. 63% of that of the corresponding aromatic thiol monolayers.³⁵ Additionally, both Au–C₁₈monoalkyne and Au–C₁₈trialkyne displayed slightly lower SWCAs than Au–C₁₈alkyne, in line with the presence of the polar amide group.

Next, the morphologies of formed monolayers were characterized by AFM (Figure 1B). The roughness of the four different monolayers did not exhibit significant changes compared to the freshly cleaned Au substrate (1.0 nm \pm 0.8 nm), which indicates that the formed monolayers uniformly cover the gold substrate surface with excellent homogeneity.

3.2. Bonding Motif Comparison. *3.2.1. Hydrolytic Stability.* As sensors (with their sensing surfaces) often operate while immersed in aqueous solutions, the hydrolytic stability of interfaces plays a crucial role in withstanding the challenges presented by complex matrices in which they should operate. To compare the hydrolytic stability of alkyl thiolate and terminal alkyne monolayers, modified Au surfaces were immersed in four different aqueous environments for a continuous duration of 7 days with constant agitation. These solutions were MQ-water, simulated intestinal fluid (SIF, pH 7) given our interest in developing gut biosensors, aqueous HCl solution (pH 3), and aqueous NaOH solution (pH 11).



Figure 1. (A) XPS wide scan and (B) AFM tapping mode images (scale bar = 200 nm) of the piranha solution-cleaned Au substrate and four different monolayers formed on the Au substrate.



Figure 2. Hydrolytic stability of alkyl SAMs in various aqueous media. (A, B) SWCA measurements, (C, D) normalized XPS C 1s/Au 4f signal ratios, (E) XPS O 1s/C 1s signal ratios, and (F, G) C 1s XPS narrow-scan spectrum for $Au-C_{18}SH$ and $Au-C_{18}alkyne$, respectively. Measurements were performed after taking out the samples at the indicated time points from MQ-water, SIF (pH 7), HCl solution (pH 3), and NaOH solution (pH 11).

After 0, 1, and 7 days, the surfaces were taken out and were rinsed and dried, and changes in surface wettability were assessed through SWCA measurements, while XPS measurements were used to analyze the variation in the C 1s/Au 4f ratio to independently monitor changes in monolayer quality.^{46,47}

The hydrolytic stability results of $Au-C_{18}SH$ and $Au-C_{18}alkyne$ as characterized by SWCA measurement are shown in Figure 2A,B. It was found that no significant changes in the surface wettability were observed for the $Au-C_{18}SH$ surfaces after immersion in the four different aqueous media for 7 days. This result is consistent with the reported good hydrolytic



Figure 3. Thermal stability of alkyl SAMs at 80 °C. (A) SWCA and (B) XPS elemental composition for $Au-C_{18}SH$ and $Au-C_{18}alkyne$ before and after heating at 80 °C for 1 and 16 h, respectively.

stability of $Au-C_{18}SH$, which exhibited only 8 and 3° decreases in SWCA after immersion in 1 N HCl and 1 N NaOH for 1 month, respectively.⁴⁷ For $Au-C_{18}$ alkyne, a slight decline in hydrophobicity could be observed after 7 days of immersion: the SWCA decreased to $93 \pm 5^{\circ}$ in MQ-water, to 95 \pm 3° in SIF, to 99 \pm 3° in HCl, and to 97 \pm 1° in NaOH, respectively, from its original value of $102 \pm 2^{\circ}$. The results indicated that some deterioration in the integrity of monolayers had occurred, but also that such changes are likely acceptable given the usage time of most biosensors, such as the transportation times of pill-embedded ingestible sensors traveling through the human gastrointestinal (GI) tract. The changes in the XPS C 1s/Au 4f signal ratio shown in Figure 2C,D for Au-C₁₈SH and Au-C₁₈alkyne, respectively, allow for a further understanding of the effect of immersion on the monolayer. Aligning with the stability results from the SWCA measurement, the C 1s/Au 4f signal ratios of $Au-C_{18}SH$ also remained constant over time, suggesting the monolayer was highly stable under all the investigated conditions. This corresponds to the reported research findings of other thiolates SAM on Au in Tris-buffered saline, which showed nearconstant C 1s/Au 4f signal ratios over 7 days.⁴⁸ For the Au-C18alkyne in all media a slight decrease in the C 1s/Au 4f signal ratio was observed from day 0 to day 7, with a good retention of the monolayer quality on both MQ water (95 \pm 6% of original C 1s/Au 4f signal ratio) and SIF (94 \pm 7%), whereas a week in HCl or NaOH decreased this ratio to 87 \pm 7 and 87 \pm 5%, respectively. This indicates two things: (1) the terminal alkyne SAMs are slightly less resistant to harsh conditions, such as acidic or basic solutions; (2) their stability is likely more than enough for pill-embedded ingestible sensors.

This difference in monolayer stability is attributed to the oxidation of the SAMs. Oxygen-containing species have been reported to form during the formation of acetylenylbenzene monolayers on gold substrates, possibly resulting from gold-catalyzed reactions with ambient oxygen.⁴⁹ Although this process was suppressed by preparing terminal alkyne monolayers in an O₂-free glovebox, achieving a low O 1s/C 1s signal ratio (0.04 ± 0.03), oxidation can still happen after SAM formation.³² Hence, we investigated the variation of O 1s/C 1s signal ratios in the two types of SAMs in the four different media over time. Figure 2E shows that the oxygen content in Au-C₁₈SH remained almost unchanged over 7 days, likely due to the ordered structure of the Au-C₁₈SH

monolayer film enhancing its oxidation resistance.¹⁷ However, in the case of $Au-C_{18}$ alkyne, there were visible increases in the O 1s/C 1s signal ratios, which rose from their initial value of 0.04 \pm 0.03 to values ranging from 0.08 \pm 0.01 to 0.12 \pm 0.02 in different media after 7 days. Apart from analyzing the O 1s/C 1s ratio in the survey scans, the corresponding C 1s narrow scans were also measured to better understand the (change in) monolayer composition. Figure 2F,G exhibits a comparison in the XPS C 1s narrow scan from these two monolayers. The C 1s narrow scan for Au-C₁₈SH remained unchanged across four different aqueous media over 7 days, while for Au-C18alkyne, new carbon peaks with higher binding energies ranging between 285.5 and 289.0 eV appeared, which are assigned to oxidized carbon atoms.⁴⁹ This comparison implies that terminal alkyne monolayers on Au exhibit a higher susceptibility to oxidation than thiolate monolayers, probably due to a lower oxidation potential of the Au–C \equiv C moiety (see below) and the lower packing density; the first is related to the nature of the weakened $C \equiv C$ bonds caused by the back-donation of electrons from the d-orbitals of Au to the π^* orbital of alkyne.^{34,50} In addition, the lower packing density of the formed monolayers may raise the likelihood of contact between oxidants (like O2) and the headgroup-substrate interface.⁵¹

3.2.2. Thermal Stability. Following the hydrolytical stability tests, the thermal stability of the monolayers was investigated under atmospheric conditions. Considering that most biosensors generally operate at relatively low temperatures (20-37 °C), SAMs were heated to 80 °C for 1 and 16 h, respectively, to rapidly obtain thermal stability data. After heating, the samples were cleaned by rinsing with MQ-water, sonicating in ethanol for 10 s, and then rinsing with DCM before being dried with Ar. Figure 3A shows that both Au- $C_{18}SH$ and $Au-C_{18}alkyne$ exhibited nearly unchanged SWCAs after 1 h at 80 °C. Analogously, Figure 3B indicates that the elemental compositions of Au-C₁₈SH also remained constant. Meanwhile, for Au-C₁₈alkyne, the XPS C 1s signal ratio exhibited slight changes after heating at 80 °C for 1 h, while the XPS O 1s signal increased from 2 ± 1 to $4 \pm 1\%$, indicating that the SAM underwent slight oxidation at elevated temperatures. That all layers eventually oxidized became more obvious after heating for 16 h at 80 °C, when an obvious deterioration in both $Au-C_{18}SH$ and $Au-C_{18}alkyne$ was observed (see Figure 3B). This is further supported by the appearance of peaks at around 289.1 ev of oxygen-containing species in the C 1s narrow scan spectrum (see SI Figure S15). These data show that long-term storage at room temperature is preferred for both types of SAMs and that prolonged heating deteriorates the quality.

3.2.3. Electrochemical Stability. SAM-modified Au electrodes were used as working electrodes in CV experiments to characterize their electrochemical stability, by sweeping from 0 to 1.5 V in 0.1 M aqueous H_2SO_4 solution to investigate and compare their oxidative desorption potentials. As shown in Figure 4, an oxidation peak was observed at ~1.37 V for the



Figure 4. Cyclic voltammograms for $Au-C_{18}SH$ and $Au-C_{18}alkyne$ in an aqueous electrolyte of 0.1 M H_2SO_4 at a scan rate of 0.05 V/s.

bare Au electrode, corresponding to the oxidation of the Au substrate, while the reductive peak at ~0.90 V during the reverse sweep is attributed to the electrochemical reduction of the oxidized Au substrate.⁵² CV scans of C₁₈SH-modified electrodes show a lower current compared to bare Au electrodes, as the SAMs inhibit redox reactions. The significant oxidative current for $Au-C_{18}SH$ occurred at a higher potential compared to the oxidation peak of the Au substrate (>1.5 eV), consistent with the reported data for SAMs of 1-propanethiol.⁵² Au $-C_{18}$ alkyne remained electrochemically inert up to \sim 1.20 V, with the oxidation current peaking at around 1.38 V, in alignment with the electrochemical behavior of the reported conjugated alkyne-anchored monolayers.^{36,53} The oxidative peaks in C₁₈SH and C₁₈alkyne can most likely be attributed to the electrochemical oxidation of the monolayers themselves, together with the Au substrate oxidation process, as evidenced by significant reductive peaks of gold oxide during the reverse sweeping.^{52–54} Existing research suggests that thiols are mostly likely irreversibly oxidized to oxidized sulfur species (like R-SO²⁻),^{55,56} However, for terminal alkynes, there has been no detailed study on the oxidized species and the mechanism of oxidative desorption, and further investigation is required. In summary, the obtained oxidation potentials suggest that both thiolate and alkyne SAMs-modified interfaces remain stable in a wide anodic potential window, which benefits their application in electrochemical sensors.

In summary, (monovalent) thiolate and alkyne SAMs exhibit comparable hydrolytic and thermal stabilities, demonstrating the potential of alkyne-based SAMs on gold in biosensor applications. In addition, it has been reported in the literature, that alkyne-based monolayers are more resistant to displacement by organic thiols compared to their thiol analogs,^{35,37} further demonstrating their stability and derived possibility in complex media involving thiol-containing biomolecules (like proteins). Moreover, recent studies have demonstrated that alkyne monolayers on Au exhibit superior charge transfer compared to thiolate monolayers possibly due to their moderate packing density,^{35,36} or the extension of the conductive moiety by the C \equiv C group.³⁶ This characteristic enhances their potential for application in sensor technology, particularly where efficient electron transfer is crucial, such as electrochemical sensors.

3.3. Bonding Number Comparison. To further increase the robustness of terminal alkyne-based interfaces by multivalency, we synthesized two adsorbates (see Scheme 1) with similar core and chain lengths, but varying numbers of alkyne binding sites. The straightforward synthesis primarily involved the amide formation between the appropriate amine and stearoyl chloride (see SI Scheme S1). These mono- and trivalent alkynes were used to make the corresponding monolayers under the same optimized formation conditions previously found for $Au-C_{18}alkyne$ (see above).

3.3.1. Hydrolytic Stability. Hydrolytic stability tests were similarly conducted on these two monolayers, by immersion in MQ-water, SIF (pH 7), HCl solution (pH 3) or NaOH solution (pH 11) for up to 7 days. As shown in Figure 5B, the contact angles of Au-C18trialkyne remained practically constant over 7 days across four different solutions. In contrast, the SWCA of the Au-C₁₈monoalkyne (see Figure 5A) showed a visible decrease from 1 to 7 days in all four different solutions. Specifically, the SWCA decreased from 101 \pm 3 to 93 \pm 4° in water, to 80 \pm 13° in SIF, to 74 \pm 3° in HCl, and to 91 \pm 8° in NaOH. Additionally, XPS analysis was used to quantitatively monitor monolayer changes. The Au-C₁₈trialkyne (see Figure 5D) showed relatively minor variation in the normalized XPS C 1s/Au 4f signal ratio (referenced to freshly prepared monolayers), remaining $88 \pm$ 12% in MQ-water, 91 \pm 10% in SIF, 85 \pm 11% in HCl, and 76 \pm 8% in NaOH after 7-day immersion. In contrast, the Au- C_{18} monoalkyne (see Figure 5C) only displayed a stable ratio in MQ-water after 7-day immersion, with about $91 \pm 1\%$ of its original signal ratio maintained, but the monolayer was basically destroyed in the other media C 1s/Au 4f signal ratios between 29 and 54%. These results indicate that the trivalent binding drastically improved the hydrolytic stability of the alkyne-based monolayers in these different media, bringing it close to even the thiol-based monolayers.

3.3.2. Thermal Stability. Figure 6A illustrates that both Au-C18monoalkyne and Au-C18trialkyne did not undergo large changes in wettability after being heated at 80 °C for 1 h and only a slight decrease after 16 h of heating. The same conclusion is also obtained more straightforwardly from the XPS elemental composition changes. The C 1s XPS spectrum (SI Figures S18 and S19) provided additional details: the peak area of peaks at ~286.5 and ~288.5 eV showed a slight increase compared to their original monolayers, indicating partial oxidation under heating conditions, likely forming more oxygen-containing species with C-O or C=O bonds. Interestingly, compared to the previously discussed Au-C18alkyne, not only the tridentate Au-C18trialkyne showed better heat resistance due to its multivalent binding, but the monodentate Au-C₁₈monoalkyne also exhibited improved thermal stability. This may be attributed to the stabilizing effect of intermolecular hydrogen bonds formed within the



Figure 5. Hydrolytic stability of mono- and trivalent alkyne monolayers in various aqueous media. (A, B) SWCA and (C, D) normalized XPS C 1s/ Au 4f signal ratios for $Au-C_{18}$ monoalkyne and $Au-C_{18}$ trialkyne, respectively. Measurements were performed after taking out the samples at the indicated time points from MQ-water, SIF (pH 7), HCl solution (pH 3), and NaOH solution (pH 11).



Figure 6. Thermal stability of mono- and trivalent alkyne monolayers at 80 °C. (A) SWCA measurements and (B) XPS elemental composition for $Au-C_{18}$ monoalkyne and $Au-C_{18}$ trialkyne heated at 80 °C for 1 and 16 h.

 $Au-C_{18}monoalkyne$ backbone due to the presence of amide bonds.^{57,58}

3.3.3. Electrochemical Stability. Cyclic voltammetry was also used to investigate the oxidative desorption process of $Au-C_{18}monoalkyne$ and $Au-C_{18}trialkyne$, as shown in Figure 7. These two modified Au electrodes exhibited a similar electrochemical oxidative behavior as $Au-C_{18}alkyne$: significant oxidation peaks only appeared at a higher voltage than bare gold oxidation, more specifically, ~1.40 V for $Au-C_{18}monoalkyne$ and ~1.48 V for $Au-C_{18}trialkyne$, while the reductive peaks of oxidized gold appeared during the reverse sweep indicating that the oxidation of the monolayers

themselves is accompanied by Au oxidation. Our results demonstrate that these functionalized alkyne adsorbates possess an electrochemical potential window similar to alkyl alkyne (C_{18} alkyne), which enables their application in a wide range of biosensors, and thereby their integration with recognition units (like enzymes) and attaching antifouling coatings through surface-initiated polymerization methods.

4. CONCLUSIONS

Detailed comparative studies reveal that monovalent alkynebased monolayers on Au can rival their thiol-based analogs in terms of hydrolytic stability upon prolonged immersion (7



Figure 7. Cyclic voltammograms for $Au-C_{18}monoalkyne$ and $Au-C_{18}trialkyne$ in an aqueous electrolyte of 0.1 M H₂SO₄ at a scan rate of 0.05 V/s.

days) in four different aqueous media. Moreover, they also possess similar thermal stability when heated for 1 h at an elevated temperature (80 °C). Additionally, the multivalent effect of the tridentate structure was found to starkly improve both long-term hydrolytic stability and thermal stability of alkyne-based monolayers. Moreover, alkyne-based and thiolate monolayers exhibit higher oxidation potentials than bare Au electrodes, enabling their further application in practical biosensing when combined with recognition units, such as enzymes or antibodies, allowing for real-world sensing in complex media such as bioreactors or bodily fluids. Overall, our findings underscore the advantages of terminal alkyne SAMs in sensor technology. Particularly, the integrated capability of their long-term hydrolytic stability, thermal stability, the reported efficient electron transfer, integration with various recognition units and inertness toward (bio)thiols substitution all position alkyne-based monolayers as valuable candidates for advanced biosensor development.

ASSOCIATED CONTENT

Supporting Information

The Supporting Information is available free of charge at https://pubs.acs.org/doi/10.1021/acs.langmuir.4c05211.

Detailed synthetic protocols and characterization data (¹H and ¹³C NMR spectrum and MS) for adsorbates; diagram for surface cleaning method comparison; diagram for thermal stability of $Au-C_{18}SH$ and $Au-C_{18}alkyne$ at various temperatures; and XPS C 1s narrow spectra for different monolayers (PDF)

AUTHOR INFORMATION

Corresponding Authors

- Maarten M. J. Smulders Laboratory of Organic Chemistry, Wageningen University and Research, 6708WE Wageningen, The Netherlands; Ocicid.org/0000-0002-6855-0426; Email: maarten.smulders@wur.nl
- Han Zuilhof Laboratory of Organic Chemistry, Wageningen University and Research, 6708WE Wageningen, The Netherlands; School of Pharmaceutical Sciences and Technology, Tianjin University, Tianjin 300072, P. R. China; College of Biological and Chemical Engineering, Jiaxing

University, Jiaxing 314001, P. R. China; orcid.org/0000-0001-5773-8506; Email: han.zuilhof@wur.nl

Authors

- Zhen Yang imec within OnePlanet Research Center, 6708 WH Wageningen, The Netherlands; Laboratory of Organic Chemistry, Wageningen University and Research, 6708WE Wageningen, The Netherlands; © orcid.org/0009-0006-2764-5556
- Sidharam P. Pujari Laboratory of Organic Chemistry, Wageningen University and Research, 6708WE Wageningen, The Netherlands; • orcid.org/0000-0003-0479-8884
- **Rachel Armstrong** imec within OnePlanet Research Center, 6708 WH Wageningen, The Netherlands
- Klaus Mathwig imec within OnePlanet Research Center, 6708 WH Wageningen, The Netherlands; • orcid.org/ 0000-0002-8532-8173
- Floris P. J. T. Rutjes Institute for Molecules and Materials, Radboud University, 6525 AJ Nijmegen, The Netherlands; orcid.org/0000-0003-1538-3852

Complete contact information is available at: https://pubs.acs.org/10.1021/acs.langmuir.4c05211

Notes

The authors declare no competing financial interest.

ACKNOWLEDGMENTS

The authors thank Ms. Yu Han (Wageningen University) for her assistance with mass spectrometry measurements and Dr. Francesca Leonardi (imec within OnePlanet Research Center) for her valuable feedback on the electrochemical stability section. We acknowledge financial support from the Province of Gelderland and from a Top-level Talent Project of Zhejiang Province (Jiaxing University, to H.Z.).

REFERENCES

(1) Bhalla, N.; Jolly, P.; Formisano, N.; Estrela, P. Introduction to biosensors. *Essays. Biochem.* **2016**, *60* (1), 1–8.

(2) Wisniewski, N.; Reichert, M. Methods for reducing biosensor membrane biofouling. *Colloids Surf. B Biointerfaces* **2000**, *18* (3–4), 197–219.

(3) Erathodiyil, N.; Chan, H. M.; Wu, H.; Ying, J. Y. Zwitterionic polymers and hydrogels for antibiofouling applications in implantable devices. *Mater. Today* **2020**, *38*, 84–98.

(4) Frutiger, A.; Tanno, A.; Hwu, S.; Tiefenauer, R. F.; Vörös, J.; Nakatsuka, N. Nonspecific Binding-Fundamental Concepts and Consequences for Biosensing Applications. *Chem. Rev.* **2021**, *121* (13), 8095–8160.

(5) Ko, Y.; Truong, V. K.; Woo, S. Y.; Dickey, M. D.; Hsiao, L.; Genzer, J. Counterpropagating Gradients of Antibacterial and Antifouling Polymer Brushes. *Biomacromolecules* **2022**, 23 (1), 424–430.

(6) Paschke, S.; Prediger, R.; Lavaux, V.; Eickenscheidt, A.; Lienkamp, K. Stimulus-Responsive Polyelectrolyte Surfaces: Switching Surface Properties from Polycationic/Antimicrobial to Polyzwitterionic/Protein-Repellent. *Macromol. Rapid Commun.* **2021**, 42 (18), No. 2100051.

(7) Kuzmyn, A. R.; Teunissen, L. W.; Fritz, P.; van Lagen, B.; Smulders, M. M. J.; Zuilhof, H. Diblock and Random Antifouling Bioactive Polymer Brushes on Gold Surfaces by Visible-Light-Induced Polymerization (SI-PET-RAFT) in Water. *Adv. Mater. Interfaces* **2022**, 9 (3), No. 2101784.

(8) Zhou, L.; Li, X. R.; Zhu, B. Y.; Su, B. An Overview of Antifouling Strategies for Electrochemical Analysis. *Electroanalysis* **2022**, *34* (6), 966–975.

(9) Vaisocherová, H.; Yang, W.; Zhang, Z.; Cao, Z. Q.; Cheng, G.; Piliarik, M.; Homola, J.; Jiang, S. Y. Ultralow fouling and functionalizable surface chemistry based on a zwitterionic polymer enabling sensitive and specific protein detection in undiluted blood plasma. *Anal. Chem.* **2008**, *80* (20), 7894–7901.

(10) Mandler, D.; Kraus-Ophir, S. Self-assembled monolayers (SAMs) for electrochemical sensing. *J. Solid. State. Electr.* **2011**, *15* (7–8), 1535–1558.

(11) Ting, B. P.; Zhang, J.; Gao, Z. Q.; Ying, J. Y. A DNA biosensor based on the detection of doxorubicin-conjugated Ag nanoparticle labels using solid-state voltammetry. *Biosens. Bioelectron.* **2009**, 25 (2), 282–287.

(12) Sulak, M. T.; Gökdogan, Ö.; Gülce, A.; Gülce, H. Amperometric glucose biosensor based on gold-deposited poly-vinylferrocene film on Pt electrode. *Biosens. Bioelectron.* **2006**, *21* (9), 1719–1726.

(13) Won, Y. H.; Huh, K.; Stanciu, L. A. Au nanospheres and nanorods for enzyme-free electrochemical biosensor applications. *Biosens. Bioelectron.* **2011**, 26 (11), 4514–4519.

(14) Vericat, C.; Vela, M. E.; Benitez, G.; Carro, P.; Salvarezza, R. C. Self-assembled monolayers of thiols and dithiols on gold: new challenges for a well-known system. *Chem. Soc. Rev.* **2010**, *39* (5), 1805–1834.

(15) Sassolas, A.; Blum, L. J.; Leca-Bouvier, B. D. Immobilization strategies to develop enzymatic biosensors. *Biotechnol. Adv.* **2012**, *30* (3), 489–511.

(16) Jans, K.; Bonroy, K.; De Palma, R.; Reekmans, G.; Jans, H.; Laureyn, W.; Smet, M.; Borghs, G.; Maes, G. Stability of mixed PEOthiol SAMs for biosensing applications. *Langmuir* **2008**, *24* (8), 3949–3954.

(17) Schoenfisch, M. H.; Pemberton, J. E. Air stability of alkanethiol self-assembled monolayers on silver and gold surfaces. *J. Am. Chem. Soc.* **1998**, *120* (18), 4502–4513.

(18) Flynn, N. T.; Tran, T. N. T.; Cima, M. J.; Langer, R. Long-term stability of self-assembled monolayers in biological media. *Langmuir* **2003**, *19* (26), 10909–10915.

(19) Asyuda, A.; Das, S.; Zharnikov, M. Thermal Stability of Alkanethiolate and Aromatic Thiolate Self-Assembled Monolayers on Au(111): An X-ray Photoelectron Spectroscopy Study. *J. Phys. Chem.* C 2021, 125 (39), 21754–21763.

(20) Willey, T. M.; Vance, A. L.; van Buuren, T.; Bostedt, C.; Terminello, L. J.; Fadley, C. S. Rapid degradation of alkanethiol-based self-assembled monolayers on gold in ambient laboratory conditions. *Surf. Sci.* **2005**, *576* (1–3), 188–196.

(21) Gao, X. N.; Jiang, L. L.; Hu, B.; Kong, F. P.; Liu, X. J.; Xu, K. H.; Tang, B. Au-Se-Bond-Based Nanoprobe for Imaging MMP-2 in Tumor Cells under a High-Thiol Environment. *Anal. Chem.* **2018**, *90* (7), 4719–4724.

(22) Hu, B.; Kong, F. P.; Gao, X. N.; Jiang, L. L.; Li, X. F.; Gao, W.; Xu, K. H.; Tang, B. Avoiding Thiol Compound Interference: A Nanoplatform Based on High-Fidelity Au-Se Bonds for Biological Applications. *Angew. Chem., Int. Ed.* **2018**, *57* (19), 5306–5309.

(23) Chinwangso, P.; Jamison, A. C.; Lee, T. R. Multidentate Adsorbates for Self-Assembled Monolayer Films. *Acc. Chem. Res.* **2011**, 44 (7), 511–519.

(24) Lee, H. J.; Jamison, A. C.; Lee, T. R. Two Are Better than One: Bidentate Adsorbates Offer Precise Control of Interfacial Composition and Properties. *Chem. Mater.* **2016**, *28* (15), 5356–5364.

(25) Park, C. S.; Lee, H. J.; Jamison, A. C.; Lee, T. R. Robust Thick Polymer Brushes Grafted from Gold Surfaces Using Bidentate Thiol-Based Atom-Transfer Radical Polymerization Initiators. *ACS Appl. Mater. Interfaces* **2016**, *8* (8), 5586–5594.

(26) Chen, W. B.; Widawsky, J. R.; Vázquez, H.; Schneebeli, S. T.; Hybertsen, M. S.; Breslow, R.; Venkataraman, L. Highly Conducting π -Conjugated Molecular Junctions Covalently Bonded to Gold Electrodes. J. Am. Chem. Soc. **2011**, 133 (43), 17160–17163.

(27) Cheng, Z. L.; Skouta, R.; Vazquez, H.; Widawsky, J. R.; Schneebeli, S.; Chen, W.; Hybertsen, M. S.; Breslow, R.; Venkataraman, L. In situ formation of highly conducting covalent Au-C contacts for single-molecule junctions. *Nat. Nanotechnol.* **2011**, 6 (6), 353–357.

(28) Crudden, C. M.; Horton, J. H.; Ebralidze, I. I.; Zenkina, O. V.; McLean, A. B.; Drevniok, B.; She, Z.; Kraatz, H. B.; Mosey, N. J.; Seki, T.; et al. Ultra stable self-assembled monolayers of N-heterocyclic carbenes on gold. *Nat. Chem.* **2014**, *6* (7), 409–414.

(29) Kaur, G.; Thimes, R. L.; Camden, J. P.; Jenkins, D. M. Fundamentals and applications of N-heterocyclic carbene functionalized gold surfaces and nanoparticles. *Chem. Commun.* **2022**, 58 (95), 13188–13197.

(30) Engel, S.; Fritz, E. C.; Ravoo, B. J. New trends in the functionalization of metallic gold: from organosulfur ligands to N-heterocyclic carbenes. *Chem. Soc. Rev.* **2017**, *46* (8), 2057–2075.

(31) Zhang, S.; Chandra, K. L.; Gorman, C. B. Self-assembled monolayers of terminal alkynes on gold. J. Am. Chem. Soc. 2007, 129 (16), 4876–4877.

(32) Zaba, T.; Noworolska, A.; Bowers, C. M.; Breiten, B.; Whitesides, G. M.; Cyganik, P. Formation of Highly Ordered Self-Assembled Monolayers of Alkynes on Au(111) Substrate. J. Am. Chem. Soc. **2014**, 136 (34), 11918–11921.

(33) Li, Y.; Calder, S.; Yaffe, O.; Cahen, D.; Haick, H.; Kronik, L.; Zuilhof, H. Hybrids of Organic Molecules and Flat, Oxide-Free Silicon: High-Density Monolayers, Electronic Properties, and Functionalization. *Langmuir* **2012**, *28* (26), 9920–9929.

(34) Maity, P.; Takano, S.; Yamazoe, S.; Wakabayashi, T.; Tsukuda, T. Binding Motif of Terminal Alkynes on Gold Clusters. *J. Am. Chem. Soc.* **2013**, *135* (25), 9450–9457.

(35) Weston, R. P.; Chen, Y. F.; Dzwonczyk, T. J.; Veras, J. A.; Sevigny, A. M.; Landis, E. C. Electrically Transmissive and Stable Alkyne-Derived Molecular Layers on Nanoporous Gold. *J. Phys. Chem. C* 2022, 126 (23), 9673–9682.

(36) Herrer, L.; González-Orive, A.; Marqués-González, S.; Martín, S.; Nichols, R. J.; Serrano, J. L.; Low, P. J.; Cea, P. Electrically transmissive alkyne-anchored monolayers on gold. *Nanoscale* **2019**, *11* (16), 7976–7985.

(37) Zhang, C. P.; Liu, Z. C.; Zhang, L. M.; Zhu, A. W.; Liao, F. M.; Wan, J. J.; Zhou, J.; Tian, Y. A Robust Au-C \equiv C Functionalized Surface: Toward Real-Time Mapping and Accurate Quantification of Fe²⁺ in the Brains of Live AD Mouse Models. *Angew. Chem., Int. Ed.* **2020**, 59 (46), 20499–20507.

(38) Pujari, S. P.; Scheres, L.; Weidner, T.; Baio, J. E.; Stuart, M. A. C.; van Rijn, C. J. M.; Zuilhof, H. Covalently Attached Organic Mono layers onto Silicon Carbide from 1-Alkynes: Molecular Structure and Tribological Properties. *Langmuir* **2013**, *29* (12), 4019–4031.

(39) Minekus, M.; Alminger, M.; Alvito, P.; Ballance, S.; Bohn, T.; Bourlieu, C.; Carriere, F.; Boutrou, R.; Corredig, M.; Dupont, D.; et al. A standardised static in vitro digestion method suitable for food an international consensus. *Food Funct.* **2014**, *5* (6), 1113–1124.

(40) Karpovich, D. S.; Blanchard, G. J. Direct Measurement of the Adsorption-Kinetics of Alkanethiolate Self-Assembled Monolayers on a Microcrystalline Gold Surface. *Langmuir* **1994**, *10*, 3315–3322.

(41) Raiber, K.; Terfort, A.; Benndorf, C.; Krings, N.; Strehblow, H. H. Removal of self-assembled monolayers of alkanethiolates on gold by plasma cleaning. *Surf. Sci.* **2005**, *595* (1–3), *56*–63.

(42) Ron, H.; Matlis, S.; Rubinstein, I. Self-assembled monolayers on oxidized metals. 2. Gold surface oxidative pretreatment, monolayer properties, and depression formation. *Langmuir* **1998**, *14* (5), 1116–1121.

(43) Tsai, H. C.; Hu, E.; Perng, K.; Chen, M. K.; Wu, J. C.; Chang, Y. S. Instability of gold oxide Au_2O_3 . Surf. Sci. 2003, 537 (1–3), L447–L450.

(44) Tsai, M. Y.; Lin, J. C. Preconditioning gold substrates influences organothiol self-assembled monolayer (SAM) formation. *J. Colloid Interface Sci.* **2001**, 238 (2), 259–266.

(45) Park, J. S.; Vo, A. N.; Barriet, D.; Shon, Y. S.; Lee, T. R. Systematic control of the packing density of self-assembled monolayers using bidentate and tridentate chelating alkanethiols. *Langmuir* **2005**, *21* (7), 2902–2911.

(46) Chandekar, A.; Sengupta, S. K.; Whitten, J. E. Thermal stability of thiol and silane monolayers: A comparative study. *Appl. Surf. Sci.* **2010**, *256* (9), 2742–2749.

(47) Bain, C. D.; Troughton, E. B.; Tao, Y. T.; Evall, J.; Whitesides, G. M.; Nuzzo, R. G. Formation of Monolayer Films by the Spontaneous Assembly of Organic Thiols from Solution onto Gold. *J. Am. Chem. Soc.* **1989**, *111* (1), 321–335.

(48) Mani, G.; Johnson, D. M.; Marton, D.; Dougherty, V. L.; Feldman, M. D.; Patel, D.; Ayon, A. A.; Agrawal, C. M. Stability of self-assembled monolayers on titanium and gold. *Langmuir* **2008**, *24* (13), 6774–6784.

(49) McDonagh, A. M.; Zareie, H. M.; Ford, M. J.; Barton, C. S.; Ginic-Markovic, M.; Matisons, J. G. Ethynylbenzene monolayers on gold: A metal-molecule binding motif derived from a hydrocarbon. *J. Am. Chem. Soc.* **200**7, *129* (12), 3533–3538.

(50) Kang, X. W.; Zuckerman, N. B.; Konopelski, J. P.; Chen, S. W. Alkyne-Stabilized Ruthenium Nanoparticles: Manipulation of Intraparticle Charge Delocalization by Nanoparticle Charge States. *Angew. Chem., Int. Ed.* **2010**, 49 (49), 9496–9499.

(51) Srisombat, L.; Jamison, A. C.; Lee, T. R. Stability: A key issue for self-assembled monolayers on gold as thin-film coatings and nanoparticle protectants. *Colloid Surface A* **2011**, 390 (1–3), 1-19.

(52) Ramos, N. C.; Medlin, J. W.; Holewinski, A. Electrochemical Stability of Thiolate Self-Assembled Monolayers on Au, Pt, and Cu. ACS Appl. Mater. Interfaces 2023, 15 (11), 14470–14480.

(53) Moneo, A.; González-Orive, A.; Bock, S.; Fenero, M.; Herrer, I. L.; Milan, D. C.; Lorenzoni, M.; Nichols, R. J.; Cea, P.; Perez-Murano, F.; et al. Towards molecular electronic devices based on 'all-carbon' wires. *Nanoscale* **2018**, *10* (29), 14128–14138.

(54) Widrig, C. A.; Chung, C.; Porter, M. D. The Electrochemical Desorption of N-Alkanethiol Monolayers from Polycrystalline Au and Ag Electrodes. *J. Electroanal. Chem.* **1991**, *310* (1–2), 335–359.

(55) Chen, Y.; Yang, C.; Wang, F. B. Electrochemical assessment of electrochemical oxidation stability of self-assembled monolayers on gold and preparation of binary self-assembled monolayers on gold. *Electrochim. Acta* **2010**, 55 (12), 3951–3956.

(56) Yang, D. F.; AlMaznai, H.; Morin, M. Vibrational study of the fast reductive and the slow oxidative desorptions of a nonanethiol self-assembled monolayer from a Au(111) single crystal electrode. *J. Phys. Chem. B* **1997**, *101* (7), 1158–1166.

(57) Son, Y. J.; Han, J. W.; Kang, H. G.; Seong, S.; Han, S. L.; Maeda, S.; Chikami, S.; Hayashi, T.; Hara, M.; Noh, J. Formation and Thermal Stability of Ordered Self-Assembled Monolayers by the Adsorption of Amide-Containing Alkanethiols on Au(111). *Int. J. Mol. Sci.* **2023**, *24* (4), 3241.

(58) Valiokas, R.; Östblom, M.; Svedhem, S.; Svensson, S. C. T.; Liedberg, B. Thermal stability of self-assembled monolayers: Influence of lateral hydrogen bonding. *J. Phys. Chem. B* **2002**, *106* (40), 10401– 10409.